This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

Val.

10

A complex comprising a magnesium dihalide and an electron donor, characterized in that it is a complex of the magnesium dihalide and the electron donor and has the following formula (I) expressing the molar ratio between the magnesium dihalide and the electron donor:

$$MgX_2 \cdot [R(OR')_n]_m$$

(I)

wherein MgX₂ is the magnesium dihalide and R(OR')_n is the electron donor, X is a halogen, R is an n-valent C₁-C₂₀ aliphatic group, an n-valent C₇-C₂₇ araliphatic group or an n-valent C₂-C₂₂ acylic group, R' is a C₁-C₂₀ alkyl group or a C₇-C₂₇ aralkyl group, n is a number from 1 to 6 and m is defined as a number $0.5 \le m \le 2.0$.

- 2. The complex according to Claim 1, characterized in that X is selected from Cl, Br and I, and is preferably Cl.
- 3. The complex according to Claim 1 or 2, characterized in that R is an n-valent C₂-C₂₂ acylic group, preferably an n-valent aromatic C₇-C₂₂ acylic group, most preferably phthaloyl.
 - 4. The complex according to Claim 1, 2-or 3, characterized in that R' is a C_6 - C_{16} alkyl group, preferably a C_6 - C_{12} alkyl group like undecyl or 2-ethyl-1-hexyl.
- 5. The complex according to any preceding claim, characterized in that n is 1 to 4, preferably about 2.0.
 - 6. The complex according to any preceding claim, characterized in that m is 0.67 to 1.0.
 - 7. The complex according to any preceding claim, characterized in that it is a magnesium dichloride phthalic acid ester complex having the formula (II):

dami

$$MgCl_2 \cdot C_6H_4(COOR')_2$$

(II)

wherein R' is the same as above.

8. The complex according to one-of-Claims 1-to-5, characterized in that it is a magnesium dichloride phthalic acid ester complex having the formula (III):

$$(MgCl_2)_3 \cdot [C_6H_4(COR')_2]_2$$

(III)

0

 α

25

5

10

wherein R' is the same as above.

claim 1

- 9. The complex according to any preceding claim, characterized in that it has an X-ray diffraction pattern showing a dominant peak at $4.5^{\circ}2\Theta$.
- 10. Process for the preparation of a complex according to any preceding claim-comprising a magnesium dihalide and an electron donor, characterized by reacting a magnesium compound (a) containing an alkoxy moiety, which magnesium compound is selected from the group consisting of a complex of a magnesium dihalide and a magnesium dialkoxide, a complex of a magnesium dihalide and an alcohol, and a non-complex magnesium dialkoxide, with a halogen compound (b), which is capable of forming the electron donor by replacement of its halogen by said alkoxy moiety.
- 11. Process according to Claim 10, characterized in that said halogen compound (b) has the formula (IV):

RXn

(IV)

- wherein R is an n-valent C₁-C₂₀ aliphatic group, an n-valent C₇-C₂₇ araliphatic group or an n-valent C₂-C₂₂ acylic group, X is a halogen and n is 1 to 6.
 - 12. The complex according to Claim 11, characterized in that R is an n-valent C₂-C₂₂ acylic group, preferably an n-valent aromatic C₇-C₂₂ acylic group, most preferably phthaloyl.
- 20 13. Process according to Claim 11 or 12, characterized in that X is selected from Cl, Br and I, and is preferably Cl.
 - 14. Process according to Claim 11, 12 or 13, characterized in that n is 1 to 4, preferably about 2.
 - 15. Process according to any of Claims 11 to 14, characterized in that said halogen compound is an organic acid halide, preferably phthalic acid dichloride Ph(COCl)₂, wherein Ph is o-phenylene.

c.101m 10

16. Process according to any of Claims 10 to 15, characterized in that said complex of a magnesium dihalide and a magnesium dialkoxide is a magnesium dichloride-magnesium dialkoxide complex of the formula (V):

 $MgCl_2 \cdot [Mg(OR')_2]_p$

(V)

25

5

wherein R' is a C₁-C₂₀ alkyl group or a C₇-C₂₇ aralkyl group, preferably a C₆-C₁₆ alkyl group, and p is 1 to 6, preferably about 2.

17. Process according to Claim 16, characterized in that said complex of a magnesium dihalide and a magnesium dialkoxide is a magnesium dichloride-dimagnesium dialkoxide complex of the formula (VI):

 $MgCl_2 \cdot [Mg(OR')_2]_2$

(VI)

wherein R' is a C₁-C₂₀ alkyl group or a C₇-C₂₇ aralkyl group, preferably a C₆-C₁₆ alkyl group.

- 18. Process according to Claim 16, characterized in that said magnesium dichloride magnesium dialkoxide complex is prepared by reacting magnesium dichloride with and alcohol into an intermediate which is a magnesium dichloride alcohol complex MgCl₂ ·(R'OH)_{2p}, wherein R' is the same as above, and reacting the magnesium dichloride alcohol complex with p mol of a magnesium dialkyl MgR"₂, wherein R" is a hydrocarbyl group having 1 to 20 carbon atoms.
- 19. Process according to Claim 18, characterized in that, independently, the molar ratio MgCl₂:R'OH is between 1:1 and 1:8, preferably between 1:2 and 1:5, the molar ratio MgCl₂ (R'OH)₂:MgR"₂ is between 1:1 and 1:4, preferably about 1:2, the temperature is between 80 °C and 160 °C, and the reaction time is about 2 h to about, 8 h.
- 20. Process according to Claim 15 and 17, characterized in that said magnesium compound (a) which is said magnesium dichloride-dimagnesium dialkoxide complex MgCl₂ [Mg(OR')₂]₂, wherein R' is a C₆-C₁₆ alkyl group, is reacted with said halogen compound (b) which is said phthalic acid dichloride Ph(COCl)₂, wherein Ph is o-phenylene.
- 25 21. Process according to any of Claims 10 to 15, characterized in that said non-complex magnesium dialkoxide has the formula (VII):

 $Mg(OR')_2$

(VII)

wherein R' is a C₁-C₂₀ alkyl group or a C₇-C₂₇ aralkyl group, preferably a C₆-C₁₆ alkyl group.

30 22. Process according to Claim 21, characterized in that said non-complex magnesium dialkoxide is prepared by reacting a magnesium dialkyl, preferably a

- Process according to Claim 15 and 21, characterized in that said magnesium compound (a) which is said non-complex magnesium dialkoxide has the formula Mg(OR')2, wherein R' is a C₁-C₂ alkyl or a C₇-C₂₇ aralkyl, preferably a C₆-C₁₆ alkyl, is reacted with said halogen compound (b) which is said phthalic acid dichloride Ph(COCl)2, wherein Ph il o-phenylene.
- 24. Process according to any of Claims 10 to 15, characterized in that said complex of a magnesium dihalide and a magnesium dialkoxide is a complex of a 10 magnesium dichloride and an alcohol having the formula (VIII):

 $MgCl_2 \cdot (R'OH)_q$

(VIII)

wherein R' is a C1-C20 alkyl group or a C7-C27 aralkyl group, preferably a C6-C16 alkyl group, and q is from 1 to 6.

- 25. Process according to Claim 24, characterized in that said complex of a 15 magnesium dihalide and an alcohol is prepared by reacting magnesium dichloride MgCl₂ and and alcohol R'OH, wherein R' is the same as above.
 - 26. Process according to Claim 24 or 25, characterized in that the reaction temperature is kept between 10 °C and 100 °C, and the reaction time is about from 10 to about 90 min.
 - 27. Process according to Claim 15 and 24, characterized in that said magnesium compound (a) which is said complex of a magnesium dihalide and an alcohol having the formula $MgCl_2 \cdot (R'OH)_q$, wherein R' is a C_1 - C_{20} alkyl or a C_7 - C_{27} aralkyl, preferably a C6-C16 alkyl, and q is from 1 to 6, is reacted with said halogen compound (b) which is said phthalic acid dichloride Ph(COCl)2, wherein Ph is ophenylene. Clamio
 - 28. Process according to one-of-Claims 10 to 27, characterized in that said magnesium compound (a) and said halogen compound (b) are reacted essentially stoichiometrically. a Jaim I
- 29. Use of a complex according to ope of Claims 1 to 9 or a complex prepared α 30 according to one of Claims 10 to 28 for the preparation of a polymerization catalyst component containing magnesium, transition metal, halogen and electron donor.

5

20

25

С

5

10

- 30. Use according to Claim 24, characterized in that said complex is reacted with a titanium halide (c).
- 31. Use according to Claim 30, characterized in that said titanium halide (c) has the formula (IX):

(OR")_pTiX₄₋₁

(IX)

wherein R'' is a C_1 - C_1 -falkyl group or a C_7 - C_{16} aralkyl group, X is a halogen and p is 0 to 3, and preferably is a titanium tetrahalide TiX_4 , wherein X is the same as above, most preferably titanium tetrachloride $TiCl_4$.

32. A complex according to one of claims 1-to-9, characterized in that it shows an IR spectra with a main absorption peak at 1729 cm⁻¹ for the C=O...Mg that has shifted 5 to 15 cm⁻¹, preferably 10 cm⁻¹ to the right, and preferably also shows three shoulders.

cloumi